

POLIGUAINA

Plastomer polymer bitumen membrane (APP)



DESCRIPTION

Prefabricated waterproofing membrane composed of distilled bitumen and plastomer polymer (APP) with rot-proof fibreglass mesh reinforcement with high dimensional stability.

Reinforcement: Fibreglass mesh

Compound: Plastomer-polymer bitumen

Upper finish: Sand

Lower finish: PE Film

Intended use: Underlayer/ Vapour barrier

Application method: Blowtorch

TECHNICAL SPECIFICATIONS

CHARACTERISTICS	TESTING METHOD	M.U.	TOLERANCE	VALUE
Thickness	EN 1849-1	mm	MDV - 0.2 mm	3
Maximum tensile strength (L/T)	EN 12311-1	N/50 mm	MDV - 20%	300/200
Flexibility at low temperature	EN 1109	°C	MLV	-5
Creep	EN 1296/1110	°C	MDV - 10°C	+120

PACKAGING

PRODUCT	ROLL SIZE	WEIGHT Kg/m ²	THICKNESS MM	SQUARE METRES PER PALLET	EN STANDARDS
Poliguaina	10 m x 1 m	2.0	-	450	13707
Poliguaina	10 m x 1 m	3.0	-	390	13707
Poliguaina	10 m x 1 m	4.0	-	300	13707
Poliguaina	10 m x 1 m		2.0	375	13707
Poliguaina	10 m x 1 m		3.0	300	13707
Poliguaina	10 m x 1 m		4.0	250	13707

Please refer to the technical data sheet for more information, constant research in the field may result in changes to data content without the producer being obliged to inform all interested parties